

**6. SPECIFICATIONS FOR POLYETHYLENE
(PE) PIPES, FITTINGS, SPECIALS &
ACCESSORIES FOR WATER SUPPLY**

**SPECIFICATIONS FOR POLYETHYLENE (PE) PIPES, FITTINGS, SPECIALS,
ACCESSORIES,**

TABLE OF CONTENTS

GENERAL	<u>PAGE NUMBER</u>
1 Ambient Conditions	6 - 2
2 Suitability for Potable Water	6 - 2
3 Definitions	6 - 2
4 Materials	6 - 2
5 Inspection and Testing	6 - 2
6 Marking of Pipes, Fittings valves and Specials	6 - 3
7 Protection during Delivery	6 - 6
8 Storing handling and hauling of Pipes, Fittings and Specials	6 - 6
9 Packing of bolts, joint rings and gaskets	6 - 11
10 Manufacturer's Certificate	6 - 11
11 Quality and workmanship	6 - 11

GENERAL

1. Ambient Conditions

All items of materials and equipment shall be in every respect suitable for storage, installation, use and operation in the conditions of temperature and humidity appertaining in Sri Lanka.

The annual average temperature is 35⁰C while the relative humidity varies generally from 70% during the day to 90% at night. The pH of water to be conveyed ranges from 6.5 – 7.9.

The climate of Sri Lanka is at times, hot and the sunlight is intense. Ambient temperature of up to 40⁰C is possible and surfaces exposed to the sunlight may rise to even higher temperatures.

2. Suitability for Potable Water

Pipes and pipeline components, including their protective coatings and joint materials, that will or may come into contact with potable water shall not constitute a toxic hazard; shall not support microbial growth; shall not cause taste or odour, cloudiness or discolouration of the water and shall be approved by recognized certifying authority listed below, as being suitable for using portable water supply schemes.

NSF International, World Headquarters, 789 N. Dixboro Road, Ann Arbor, MI 48105 USA

Water Regulations Advisory Scheme, Fern Close, Pen-Y-Fan Industrial Estate, Oakdale, Gwent, UK, NP11 3EH

IAPMO Research & Testing, 5001 E, Philadelphia St., Ontario, CA 91761-USA

3. Definitions

The definitions given in the relevant standards which are referred to in the specification shall apply for the terms used in this specification.

4. Materials

All pipes & fittings shall be of blue colour and shall comply to the Clause 5 of the Technical Specification hereof.

5. Inspection and Testing

The Contractor shall supply, furnish and prepare the necessary test pieces and samples of all materials and supply the labour facilities and appliances for such testing as may be required to be carried out on his premises according to this specification. If there are no facilities at his own works for making the prescribed tests the Contractor shall bear the cost of carrying out the tests elsewhere.

The Engineer or his representative or nominated inspection authority shall have full access to all parts of the plant that are concerned with the testing, furnishing or preparation of materials for the performance and testing of work under this Specification.

The Contractor shall furnish the Engineer or his representative or nominal inspection authority with reasonable facilities and space (without charge) for the inspection, testing and obtaining of such information, as he desires regarding the character of material in use and the progress and manner of the work.

The manufacturer shall provide results of tests conducted, in accordance with the BSEN or ISO standards given in the Specification.

6. Marking of Pipes, Fittings and Specials

All markings described below shall be legible and indelible unless otherwise specified.

All pipes and fittings shall be marked as specified in clause 8 of ISO 4427 : 1996 (E) or BSEN 12201-2:2003 and as specified in the Table 1 hereof. The manufacturer's name Identification mark and the PN rating shall be marked legibly and indelibly on the pipes together with the information shown below.

Markings should be in such a way that it does not initiate cracks or other types of failures and that normal storage, weathering, handling, installation and use shall not affect the legibility of the markings.

During the manufacturing process, the pipe should be marked with pertinent product and process information at approximately 1m intervals along the pipe.

Specifications require at least the following information to be included.

- Manufacturer's identification or logo,
- Standard number (Specification number)
- The designation of the pipe material (PE 80 or PE 100 etc.)
- The dimensions (Nominal outside diameter, nominal wall thickness)
- The outside diameter tolerance (A or B)
- Third party certification mark by the inspection agency approved by the Engineer.
- The Production Period (date and code)
- The Nominal Pressure (PN)

- Standard Dimension Ratio (SDR)

The marking should be printed in the following colours:

PE 80	SDR 11	Dark blue
	SDR 17.6	Red
PE 100	SDR 11	Black
	SDR 17.6	Red
	SDR 26	Yellow
	SDR 33	Orange

In addition to the information given in clause 7 of General Specifications following information to be marked on the fittings:

- In case of a bend, bending angle and incase of unequal tee branch line size and main line size.
- Pressure rating at relevant temperature
- Standard Dimension Ratio (SDR)
- Fusion time (Seconds)
- Cooling time (minutes)
- System voltage
- Moulded-in identification and appropriate product information
- Terminal pin size of electro fusion fittings

Table 1 - Marking

Item	Lettering Heights (mm) for pipes/fittings above 160 mm dia	Lettering Heights (mm) for pipes/fittings below 160 mm dia
Pipes		
NWSDB	50 mm dia. at 3m intervals	25 mm dia at 3m intervals
Water	50 mm dia. at 3m intervals	25 mm dia at 3m intervals
SDR	25 mm dia. at 3m intervals	15 mm dia. at 3m intervals
Manufacturing Standard	15 mm dia. at 3m intervals	15 mm dia. at 3m intervals
Outside diameter	25 mm dia. at 3m intervals	15 mm dia. at 3m intervals
Third Party Certificate Mark	50 mm dia. at 3m intervals	40 mm dia. at 3m intervals
Production Date	25 mm dia. at 3m intervals	15 mm dia. at 3m intervals
Nominal pressure	25 mm dia. at 3m intervals	15 mm dia. at 3m intervals
Other	25 mm dia. at 3m intervals	15 mm dia. at 3m intervals
Fittings		
NWSDB	50 mm dia.	25 mm dia
Water	50 mm dia.	25 mm dia
SDR	25 mm dia.	15 mm dia.
Manufacturing Standard	15 mm dia.	15 mm dia.
Outside diameter	25 mm dia.	15 mm dia.
Third Party Certificate Mark	50 mm dia.	40 mm dia.
Production Date	25 mm dia.	15 mm dia.
Nominal pressure	25 mm dia.	15 mm dia.
Other	25 mm dia.	15 mm dia.

All fittings must be packed in such a way to allow instant use on site without additional cleaning. All electro-fusion fittings must be packed in transparent protective bags. The electro-fusion fittings must then be packed in carton boxes. The Contractor shall label and clearly mark all crates and boxes legibly and indelibly as specified in the notes forming a part of this Specification.

All fittings shall be marked with the corresponding item number in the Bills of Quantities or any other number specified by the Engineer. An individual data carrier card in compliance with ISO 7810 and ISO 7811 containing a magnetic strip and appropriate bar codes as well as manual setting information for data transfer purposes must be supplied with each item as appropriately.

7. Protection during Delivery

The Contractor shall provide methodology of protection of pipes and fittings, to the approval of the Engineer and obtain written approval prior to the pipes and fittings leaving the place of manufacture and shall maintain such protection until the items reach their destination in order to guard effectively against damage during handling, transit and storage and ingress of foreign matter inside the pipes & fittings.

All fittings shall be securely packed in crates and boxes to prevent damage during delivery. The cost of packing shall be deemed to be included in the Contract Rates and crates will not be returned.

The Supplier shall provide necessary details to the shipping line on precautions to be taken during loading/unloading, handling & transport of the pipes & fittings and other components, in the sea. Supplier shall provide to the purchaser a set of recommendations of manufacturer for handling, loading, unloading, transporting and storing of polyethylene pipes and fittings.

8. Storing, Handling and Hauling of Pipes, Fittings and Specials

All materials shall be stored in an approved location and in such a manner as to preserve their quality and condition as recommended by the manufacturer.

All materials should be carefully inspected at the time of delivery and any defective material set aside before accepting the delivery into stores. Any such defects should be notified to the supplier immediately.

Materials and components shall be handled in such a manner as to avoid any damage or contamination and in accordance with all applicable manufacturers recommendations.

8.1 General Principles

The recommendations for handling and storage of PE pipes shall have greater care in the handling of PE 100 pipe coils too shall have greater care as of pipes of similar wall thickness.

Polyethylene is a tough resilient material which is relatively light and easy to handle although it is prone to damage through scoring by sharp objects. Therefore careful handling is always required and the dragging of straight pipe and coils should be avoided.

The maximum allowable depth of scoring of the external surface of the pipe is 5% of the wall thickness. Pipes and fittings showing obvious defects or excessive scoring should be withdrawn, clearly identified as unsuitable and, where appropriate, returned to the source of supply.

The general properties of polyethylene are unaffected by low ambient temperatures but, having very smooth surfaces, the pipes and fittings become slippery in wet or frosty weather. Particular attention should be given to effective securing and storage under such conditions. Extra care should also be taken when handling large diameter prefabricated fittings during very cold weather.

The packaging of pipes by the manufacturer is normally consistent with the requirement to prevent damage and to comply with safety considerations. Usually pipes are delivered strapped into convenient bundles or banded coils. Fittings are normally supplied in separate cartons together with any associated small items, such as bolts and gaskets.

As far as practicable the protective packaging (pallets, strapping, bags etc.) should be kept intact until the material is required for use. The temporary capping or plugging of pipe ends is recommended.

Pipes and fittings likely to be stored outside for periods longer than 12 months should be covered by a tarpaulin or black polyethylene sheeting to prevent ultra violet degradation from sunlight. Electro fusion fittings should be stored under cover and in their protective packaging.

For hygiene purposes, the pipe ends must be protected from the ingress of dirt/water etc. This protection should be carefully disposed of following use.

8.2 Transport and Delivery

For transporting bulk loads, vehicles should be provided with a clean flat bed, free from nails or other projections, which may cause damage. If high sided lorries are used, special care must be taken to prevent slippage or excessive bowing of the pipes and extra protection given at all sharp edges.

Care should be taken to avoid positioning pipes and fittings near or adjacent to exhaust systems or other heat sources and to avoid possible contamination from materials such as lubricating or hydraulic oils, gaseous, solvent and other aggressive chemicals.

Metal chains or slings should not be brought into direct contact with the material. Webbed slings of polypropylene or nylon are recommended. Straight pipes should be fully supported and bound together. Pipes must not rest on the integral socket, if one is incorporated.

When transporting 'pupped' fittings, these should not be loaded in a way that it could distort the pupped end.

Both vertical and horizontal deliveries of coiled pipes are permissible, although in the case of horizontal transportation special notification may be required for highway authorities in respect of wide load regulations.

Following the quality control inspection and testing, caps or plugs are to be provided to protect the jointing surfaces during transportation and storage. The finished and protected pipes are then carefully packed into manageable units (bundles or coils) prepared for shipments.

8.3 Off Loading

8.3.1 Bundled Pipes

When lifting by crane, non metallic wide band slings or ropes should be used, and for pipe lengths greater than 6m, load spreading beams of a length at least equivalent to one quarter of the length of the pipe or bundle pack should be employed.

Chains or end hooks should not be used. Care should be taken to avoid damage to pipes and pipe ends during lifting, particularly those pipes with couplers.

Some bending should be allowed for in the middle of the lift when loading and unloading pipes and, because of this, lifting points should always be well spread and evenly spaced.

Standard bundle packs, 6m long, may be handled by fork lift trucks but due allowance should be made for the flexible nature of the pipes in the positioning of the forks and the raising of the load.

Bundle packs greater than 6m long should be handled either by a side loader with a minimum of four supporting forks, or by a crane using a spreader beam and suitable slings. Individual pipes may be and led in the same way. Off-loading on site may be made easier by using skid timbers and rope slings.

8.3.2 Coiled Pipes

Pipe coils shall be transported inside containers from place of manufacture. Manufacturer/Tenderer (Contractor) shall ensure that coils of pipes are not exposed to direct sunlight at any place, during transit. Tenderer (Contractor) shall deliver the pipe containers in closed condition to purchaser's stores as directed and only inside the purchaser's warehouse, the containers shall be opened for inspection. Tenderer in coordination with the purchaser shall make arrangements for customs clearance, when the containers are brought to storage warehouse.

Reinforced adhesive tape at least 50 mm wide should be used for banding. Complete coils are secured by outer and intermediate bands and individual layers are also independently secured. These should not be removed until the pipe is required for actual use.

Pipe less than 63 mm in diameter should be moved and uncoiled using an approved dispensing trailer.

Before unstrapping pipe from the coil or drum, both pipe ends must be firmly mechanically restrained. The band securing the outer end of the pipe should be removed first and the movement of the free end carefully controlled. This removal should be followed with those securing successive layers. No more bands should be removed than necessary to release the length of pipe immediately required. After sufficient pipe has been cut from the coil the protective end cap must be replaced on the remainder. The outer end of the pipe should be suitably re-marked as such.

When removed from the coil or drum, the pipe will be oval and curved. The extent of ovality and curvature will depend upon the temperature, SDR rating, pipe diameter, coil diameter and material type. Although both ovality and curvature will reduce naturally with time, special hardware is available to facilitate handling and jointing.

(See the fig. 1 in Annex - C hereof, showing the proper handling methods for coils)

8.3.3 Fittings

Hooks should not be used to lift fittings which are generally supplied in cardboard boxes or polyethylene bags.

8.3.4 Storage at Depot

Materials of different polymer manufacture should be kept separately and clearly identified.

Blue polyethylene pipe should preferably be stored under cover and protected from direct sunlight until required for use. Where storage facilities necessitate the material to be exposed externally, suitable good protective sheeting should be used.

All pipe stacks should be made on sufficiently firm, leveled ground and free from stone to support the weight of the pipes and any necessary lifting equipment. Stacking heights should be kept to a minimum and without exceeding the

manufacturer's recommendation and adequate space allocated for lifting machinery to manoeuvre (more carefully and often with difficulty) without causing accidental damage.

For safety and the convenience of handling, the stacking height for bundles should not be more than 3 metres. To prevent possible deformation of the pipes, bundles must be stored timber to timber.

The Bidder shall make arrangements to stack wrapped/bagged coils neatly on robust pallets (free from projections), in Central Stores, conforming to the following maximum stack heights.

- 7 coils for 20 mm diameter pipe
- 6 coils for 25 mm diameter pipe
- 5 coils for 32 mm diameter pipe
- 4 coils for 50 mm diameter pipe
- 3 coils for 63 mm diameter pipe
- 2 coils for 90 mm diameter pipe
- 1 coils for 110 mm diameter pipe
- 1 coils for 125 mm diameter pipe
- 1 coils for 180 mm diameter pipe

Forklift trucks shall not be used to load and unload pipes except where coils are neatly stacked on pallets or coils and are provided with slings.

For similar reasons, pipe coils should be stored flat and the number of coils per stack should be limited to;

Where individual pipe lengths are stacked in pyramidal fashion, deformation may occur in the lower layers, particularly in warm weather. Such stacks should therefore be no more than 1 metre high. Socketed pipes should be stacked with the sockets at alternate ends and with the sockets protruding to avoid uneven stacking which may permanently distort the pipes.

Polyethylene fittings should be stored under cover, preferably on racking and in the manufacturer's protective wrapping or cartons which should be kept intact until the fitting is required for use.

At all times pipes and fittings should be stored away from exhaust outlets and all other high temperature sources. Care should also be taken to avoid contact with lubricating or hydraulic oils, gasoline, solvents and other aggressive chemicals.

All special tools and equipment associated with the jointing of PE pipes and fittings should be stored separately and securely until they are required for use. The heating faces of fusion tools should be kept in a position where the surfaces are protected from scratching or other damage. Tools incorporating cutting edges should likewise be protected from damage that could cause poor joint preparation.

9. Packing of Bolts, Joint Rings and Gaskets

Bolts of the same length and size (and their accompanying nuts and washers) shall be packed together in boxes not exceeding 100 kg. gross weight.

Joint rings and gaskets shall be packed in boxes and separate packages shall be provided for each size and description of ring or gasket.

Each box and package therein shall be clearly labeled stating the number, size and description of the contents.

10. Manufacturer's Certificate

The Contractor shall supply to the Engineer a certificate stating that each item supplied has been subjected to the tests laid down herein and conforms in all respects to this Specification or such other Specification which has been submitted to and approved by the Engineer.

11. Quality and Workmanship

All pipes, fittings and accessories shall be manufactured in compliance with the ISO 9001:2008 quality management system standards for the manufacturing factory. In addition to product quality control tests the manufacturers also must perform and satisfy long term type tests to demonstrate long term performance of pipe as detailed in relevant standards. Quality Management System Certification should be from an organization accredited to issue such certification and the manufacturer shall have this certification valid during the supply and delivery of the materials. Documentary evidence regarding accreditation together with the scope of certification should be provided.

11.1 Quality Assurance (Q/A) at Manufacturer's Works

The manufacturer shall operate a quality assurance scheme to (BS 5750 part 2), and on award of order shall submit a copy of his quality assurance guidelines, as issued to his production works sections. This shall include the following items, detailing the frequency of quality assurance checking.

- a. Raw Materials
 - i. Vetting and recording of certificates provided by the raw material manufacturer (S).
 - ii. Chemical testing of raw material and frequency of tests.

- b. Pipe Manufacture (for each pipe diameter)
 - i. Checking of extrusion compound temperature at the extruder (state the temperature) and state its consequence on quality.
 - ii. Temperature of water bath/sprayed water cooling system on extruded pipe.
 - iii. Maintenance of pull force on extruded pipe.
 - i. Procedure for resumption of production after an interruption on the production line (e.g. power failures, change of pipe production batches, etc.)
 - ii. Hourly production records.
 - iii. Frequency of calibration of testing equipments
 - iv. Inspection of stock yards (visually) and packing methods.

SPECIFICATIONS FOR POLYETHYLENE (PE) PIPES, FITTINGS, SPECIALS AND ACCESSORIES

TABLE OF CONTENTS

PAGE NUMBER

POLYETHYLENE PIPES AND FITTINGS

1	Scope	6 - 14
2	Reference Standards	6 - 14
3	Definitions	6 - 15
4	Classification	6 - 15
5	Materials	6 - 15
6	Dimensions of Pipes and Fittings	6 - 21
7	Method of Manufacture of Pipes and Fittings	6 - 22
8	Tolerances	6 - 24
9	Final Acceptance at Site	6 - 24
10	Specification for Butt Fusion Welding Machine	6 - 25
	Annex A - Characteristics of the PE compound as granules	6 - 26
	Annex B - Physical Characteristics of PE pipes	6 - 27 6 - 30
	Annex C - Sling Arrangement for Lifting 63mm dia. coils	6 - 31

POLYETHYLENE PIPES, FITTINGS, SPECIALS AND ACCESSORIES

TECHNICAL SPECIFICATION

1 Scope

This specification covers polyethylene pipes and associated fittings for the use of cold drinking water.

2 Reference Standards

ISO 4427:2007	Polyethylene (PE) pipes for water supply specifications.
EN12201-1:2003	Plastic piping System for Water Supply –Polyethylene (PE) Part 1- General
EN12201-2:2003	Part 2- Pipes
EN12201-3:2003	Part 3- Fittings
EN12201-4:2003	Part 4- Valves
EN12201-5:2003	Part 5- Fitness for purpose of the system
BSEN ISO 1167-1:2006	Thermoplastics pipes for the conveyance of fluids. Determination of the resistance to internal pressures. General Method.
BSEN ISO 1167-2:2006	Thermoplastic pipes for the conveyance of fluids. Determination of the resistance to internal pressures. Preparation of pipe pieces.
BS ISO 4065:1996	Thermoplastic pipes universal wall thickness table.
BS ISO 11922-1:1997	Thermoplastics pipes for the conveyance of fluids. Dimensions and tolerances.
BSEN 1092-1-3 BSEN 1092-2-4	Flanges & their joints, circular flanges for pipes, valves, fittings & accessories PN designated Part 1 : Steel flanges Part 2 : Cast iron flanges Part 3 : Copper alloy flanges Part 4 : Aluminium alloy flanges
BSEN 1515:2000	Flanges & their joints, bolting, selection of bolting
BSEN 1092-1:2007	Flanges & their joints circular flanges for pipes, valves, fittings & accessories PN designated steel flanges

BSEN ISO 12162:1996	Thermoplastics material for pipes and fittings for pressure applications – clarification – clarification and designation overall service (design-co-efficient).
ISO 161-1	Thermo Plastic pipes for the transport of fluids nominal out side diameter and nominal pressure
DIN 8074 August 1999	Polyethylene pipes dimensions
DIN 16963 1-15 series	Pipes joints and elements for high Density Polyethylene (PE) pressure pipe lines.
BS 7874:1998	Method of test for microbiological deterioration of elastomeric seals for joints in pipe work and pipes.
BSEN 681-1:1996	Elastomeric seals, material requirements for pipe joint seals used in water and drainage applications. Vulcanized rubber.
BSEN 681-2:2000	Elastomeric seals, material requirements for pipe joint seals used in water and drainage applications. Thermoplastic elastomers.
BS 6920	Specification for suitability of non-metallic products for use in contact with water intended for human consumption w.r.t to their effect on the quality of the water.

3. Definitions

The definitions given in the relevant standards which are referred to in the specification, shall apply for the terms used in this specification.

4. Classification

- 4.1 The terms PE 100 are a classification developed in line with a decision taken at CEN/TC 155, the European Technical Committee drafting plastics piping system standards for polyethylene products for water supply.
- 4.2 According to this classification, as detailed in ISO/DIN 12162, material has a Minimum Required Strength (MRS) value of 8 Mpa and PE 100 has a MRS value of 10 Mpa. The international Standards Organization (ISO) technical procedure ISO/TR 9080:1992 identifies these MRS values derived from the 50 year extrapolated 97.5% Lower Confidence Limit (LCL) failure stress.

5. Materials

Pipes and fittings shall be manufactured by using polyethylene as main raw material. The raw material used in manufacturing process shall be of reputed suppliers and comply with the following characteristics tabulated in Table 2 in Annex A.

5.1 Non-metallic Materials

All non-metallic materials supplied shall be in conformity with the BS 6920 Part 1 to 3:2000, BS 6920 Part 4:2001; suitability of non metallic products for use in contact with water intended for human consumption with regard to their effect on the quality of water or approved equivalent publication, as a recognized certifying authority having passed full tests of effect on water quality under the requirements for the testing of non-metallic materials for use in contact with potable water.

5.2 Pipes

Polyethylene pipes shall be flexible and in pipe form or coil form complying with standards given in the reference standards in the document. Pipe jointing methods shall be as follows.

Jointing Methods

1. Electro-fusion – Temperature, time, alignment
2. Butt-fusion – Temperature, time, alignment
3. compression – Rubber rings

5.3 Fittings

Polyethylene fittings shall be manufactured by injection moulding, factory welding or formed in the factory complying with the standards referred in the document.

Fittings shall be suitable either for electro fusion or but welding as specified in the Bill of quantities. All dimensions of electro fusion fittings must be fusible with one fusion machine.

5.3.1 Types of pipe fittings

The following types of fittings shall comply to EN 12201-3/ ISO 4427

- a) Spigot fittings
- b) Electro-fusion fittings and
- c) Mechanical fittings and joints

5.3.1.1 Spigot Fittings

Spigot fittings fall under two clauses as shown below.

Class	Description
Moulded	Injection moulded fittings
Fabricated	Fitting which are assembled using butt-fusion joints

5.3.1.2 Electro-fusion Fittings

Electro-fusion fittings shall be injection moulded fittings made of PE but incorporating integral heating element(s) to enable fusion jointing with PE pipes.

5.3.1.3 Mechanical Joints and Fittings

i. General

Metal and plastic fittings available for use with PE pipe are:

- Polymeric coated Flanged and other adaptors
- Mechanical type couplers c/w restrainer

The materials and constituent elements used in making the fitting (including elastomers, greases and any metal parts) shall be as resistant to the external and internal environments as the other elements of the piping system and shall have a life expectancy under the following conditions as least equal to that of the PE pipe confirming to EN 12201-3 or ISO 4427 with which they are intended to be used:

- a) During storage :
- b) Under the effect of the fluids being conveyed :
- c) Taking account of the service environment and operating conditions.

The requirements for the level of material performance for non-polyethylene parts shall be at least as stringent as that of the PE pipe systems.

All mechanical joints and fittings shall be of approved types designed specifically for PE pipe system. They shall be supplied with all necessary coupling, rings, nuts, bolts, washers, rubber rings/sealing gaskets and restrainers/stiffeners.

All mechanical joints, fittings and systems shall confirm to the requirements specified in BS EN 12201-5/ISO 4427 of Table below as applicable.

Characteristics for fitness for purpose of the joint, fitting of system

Characteristics	Test Method
Hydrostatic strength at room temperature	BSEN 921:1995
Cohesive resistance for Electro-fusion socket fittings for electro fusion saddle fittings	ISO 13954 ISO 13955 ISO 13956
Resistance to tensile force	ISO 13953
Mechanical Joints	
Leak tightness under internal pressure	BSEN 715
Leak tightness under internal pressure when subjected to bending (up to and including 63 mm)	BSEN 713
Plastics piping systems, Elastomeric sealing rings type joints	BSEN 911
External pressure test	
Resistance to pull out under constant longitudinal force	BSEN 712 /ISO 3501

5.3.2 Compression Fittings, Nuts for PE Pipes

Couplings, flange adaptors etc shall be compatible with the pipes specified in item 4.1 hereof; together with following;

- All bodies shall be injection moulded from recognized top quality poly propylene.
- Bodies shall be coloured black
- Bodies must have moulded in manufacturer identification, material and series information and dimension of the outside pipe diameter.
- All male and female threads shall be injection moulded to the ISO 7/1 standards.
- Nuts must have UV resistance of grade 8 of ASTM D2585.

5.3.3 Joint Rings

The physical properties of elastomeric joint rings shall comply with Table 2 of EN 681-1:1996. The joint rings shall also comply with the relevant provisions in

BS 7874:1 1998 for effects on water quality and resistance to microbiological deterioration.

Joint rings shall be supplied by the pipe manufacturer.

Each joint ring shall be marked clearly and durably in accordance with the following information in a manner that does not interfere with the sealing function of the ring, in complying with clause 10 of EN 681-1:1996.

- a). The nominal size
- b). Manufacturer's identification
- c). The number of the BS or BSEN with seal type designation
- d). Abbreviation for the elastomer

5.3.5 Flanges

All flanges dimensionally shall be in accordance with BSEN 1092: 1 to 4:Flanges and their joints and BSEN 1515:2000 1 to 2 Flanges and their joints Bolting. The screw threads in the pipes and fittings shall be complying with ISO Metric Screw Threads (ISO 7-1 and 2).

5.3.6 Flange Joints for Pipes and Pipeline Fittings

Flanges for pipes and pipeline fittings shall unless otherwise stated comply with BS 4504: section 3.1: 1989 and BSEN 1092: Part 2: 1997. Flanges shall be of PN16 nominal pressure rating and shall be raised faced, unless otherwise stated.

Flanges in accordance with BSEN 545 and ISO 2531 are dimensionally compatible with BS 4504: Section 3.1.

Flanged joints shall be complete with all nuts, bolts, gaskets and two washers per bolt.

The flanges of all fittings shall be integrally cast. The flanges of flanged pipes shall either be integrally cast or screwed or factory welded unless otherwise stated. 'Factory welded' means that the flanges are welded to the pipes at the point of manufacture under factory conditions with inspection agency certification.

The Contractor shall be responsible for checking and ensuring that mating flanges are compatible in all cases, including where connections are required to pipe work and valves associated with pumping plant and inlet/outlet pipe work at service reservoirs or other structures.

5.3.7 Steel Flange Converter

Steel Flange Converter shall be made out of polyethylene and shall conform to the EN 12201-3:2003 & EN 12201-5:2003 specification for mechanical fittings and joints including flanges for polyethylene pipes for conveyance of cold potable water for the size range 90-1000 inclusive made of metal or plastics or a combination of both.

5.3.8 Gaskets for Flanged Joints

Gaskets for flanged pipe joints shall be of the inside bolt circle type and the dimensions shall comply with BSEN 1514-2:2005 – Flanges and their joints. Dimensions of gaskets for PN-designated flanges. Spiral wound gaskets for use with steel flanges.

The physical properties of gaskets shall comply with BS 7874:1998 (Method of test for microbiological deterioration of elastomeric seals for joints in pipework and pipelines for effects on water quality and resistance to microbiological deterioration).

The Gaskets shall also comply with the relevant provisions in BS 7874:1998 for effects on water quality and resistance to microbiological deterioration.

The Gasket material shall be EPDM/SBR and shall be of average hardness of 65-75.

The Gaskets shall be supplied by the manufacturer and shall suit for PN 16 flanges unless otherwise stated.

Each gasket shall be marked clearly and durably in accordance with the following information in a manner that does not interfere with the sealing function of the gasket, in complying with clause 10 of EN 681-1:1996.

- a). The nominal size
- b). Manufacturers identification
- c). The number of the BS or BSEN with seal type designation.
- d). Abbreviation for the elastomer

5.3.9 Nuts, Bolts and Washers

The nuts, bolts and washers for flanged joints shall be of high tensile steel and shall comply with BS4395: Part 1 and 2: 1969.

The bolting shall comply with the relevant provisions of BS 4504: Section 3.1:1989.

The Bolt lengths shall be sufficient to ensure that nuts are full threaded when tightened in their final position with two threads showing.

Two washers per each bolt shall be supplied for providing under the head of the bolt and under the nut.

The bolts and nuts shall be hexagonal and shall be in accordance with BS 4190:2001 ISO metric black hexagon bolts, screws and nuts, Specification, the bolts, studs, nuts and washers used shall be made of stainless steel or hot-dipped galvanized carbon steel coated with fusion bonded epoxy powder or polyamide 11 to the finished thickness of coating between 75 m and 125 m according to WIS 4-52-03-1994. Cold applied high solid epoxy shall be used to repair the damaged coatings on the bolts and nuts after fastening.

5.4 Testing

Testing shall be carried out fully in accordance with the requirements of ISO 4427 and DIN 8075-1999 or equivalent standard acceptable to the purchaser.

Test parameters of physical and mechanical characteristics for pipes & fittings shall be as indicated in Table 3, 4, 5, 6 in Annex B.

6. Dimensions of Pipes and Fittings

Dimension of standard pipes shall conform to the following standards.

ISO 4427	PE pipes for water supply specifications
BSEN ISO 1167-1:2006 & BSEN ISO 1167-2:2006	for outside diameter & nominal pressures
ISO 161-1	Thermo Plastic pipes for the transport of fluids nominal out side diameter and nominal pressure
BS ISO 4065 – 1996	Thermoplastic pipes – universal wall thickness table
ISO 11922 – 1:1997	Thermoplastic pipes for the conveyance of fluid -

Dimensions & tolerances – Part I metric series

DIN 8074
August 1999

Polyethylene pipes dimensions

Standard lengths of a straight pipe shall be 12 m.

Dimensions of fittings shall conform to the following standards.

EN 12201-3:2003

Plastic piping System for Water Supply –
Polyethylene (PE) 3 - Fittings

DIN 16963 1-15 series

Pipes joints and elements for high Density
Polyethylene (PE) pressure pipe lines.

7. Method of Manufacturing of Pipes & Fittings

7.1 Manufacturing of PE Pipes and Fittings

7.1.1 Polyethylene are manufactured by various processes and are blended with anti-oxidants, pigments and UV stabilizers to ensure the material is suitable for use in the water industry. Amongst other factors, the range and quantities of co-monomers used can result in substantially different basic properties, e.g. melt flow rate, density, creep resistance etc.

The resulting compound is normally delivered to the manufacture in the form of granules and the PE pipes are produced by an extrusion process.

The bidder shall submit full details of manufacturing process that he intended to use with the bid.

7.2 Production Quality Control

7.2.1 The manufacture of PE pipe is a continuous processing which necessitates strict and accurate control of both materials and plant to achieve the required quality. A range of quality control tests pressures in the relevant standards should be applied within the scope of a quality assurance in accordance with BS EN ISO 9001: 2008.

7.2.2 These control procedures shall include:

- quality testing of raw materials, i.e. base compound.

- Checks on the uniformity and consistency of the granules
- control of processing parameters in terms of temperature, pressure, flow rates, haul off speed and energy input
- visual inspection of the pipes to check general appearance, dimensional compliance and any indication of inclusions or processing flaws in pipe barrels and jointing ends,
- production short term tests, to identify any variations in the plant function.

7.2.3 Essential short-term quality control tests and procedures are described in the relevant Water Industry Specifications include the following

- appearance and surface condition
- dimensions
- thermal stability
- elongation at break
- hydrostatic pressure test at 80⁰ C
- short term pressure test

7.3 Product Type Tests

7.3.2 In addition to 'production quality control' tests, there are a number of important longer-term "Type Tests" that must be undertaken to demonstrate the long-term performance of the pipe. These tests are also required whenever there is any change in such parameters as formulation, size, classification or processing technique.

7.3.3 These "Type Tests" are again detailed in the relevant specifications and include the following:

- effect on water quality
- resistance to weathering
- long term hydrostatic pressure testing
- resistance to fracture on impact tensile strength,

- elongation and weld test

7.3.4 Perhaps the most fundamental Type Test is the long term hydrostatic test which is a standard means of predicting the long-term performance of the pipe. In this test, samples are subjected different circumferential (hoop) stresses by pressurization and the subsequent time to pressure is recorded. The individual results are plotted as a log stress versus log time graph. They are then subjected to regression analysis to obtain an extrapolated 50 year stress level.

7.3.5 It is worth bearing in mind that the above requirements for long-term performance levels are minimum values and manufacturers usually ensure that their products can comfortably meet these standards, i.e. the pipes have an additional factor of safety built into them to cover any manufacturing variables.

8. Tolerances

Tolerances on wall thickness & weight, and length shall be in accordance with BS ISO 11922 - 1: 1997 or DIN 8074 1999 or ISO 4427

The tolerances on flange thickness and flange diameter shall be in accordance with BS4504: section 3.1:1989.

The tolerances on flange thickness, flange diameter and bolt holes in polyethylene Steel flange converters to be used of connecting different type of material shall conform to BS 4504:1989.

9. Final Acceptance at site

All pipes, fittings, valves and accessories shall conform to the specification at site. Engineer shall carryout necessary inspections at site prior to final acceptance.

10. Specification for Butt Fusion Welding Machine

- i. Machine shall be hydraulically operated and suitable for welding of PE pipes .
- ii. Machine shall consist of self –aligning frame and compact dimensions, to be suitable for working on narrow roads.
- iii. Machine shall comprised of four clamps in lightweight alloy of which the third one is easily adjustable in order to weld special pieces, and the automatic disconnecting devices to detach the pipes the heating mirror at the end of heating time.
- iv. Heating mirror shall be silver stone coated with electronic thermostat and separate thermometer in order to continuously check the temperature of the heating mirror. Operating electricity requirement of the heating mirror shall be 230V 50Hz.

Also it shall include removable electric facing tool complete with reducing gear, double cutting edged blades, safety micro switch all which allow the engine to start only in operating position.

- i. An electrically operated mechanical block device avoiding dislocation during the facing operation. Operating electricity requirement shall be 230V, 50Hz.
- ii. A support for facing tool and heating mirror suitable to carry the two part and to hold them when it is not in use.
- iii. Hydraulic double throw pump with precision pressure gauge (class 1.0-100 bar scale and 100mm face to easy reading) incorporates a device which maintains pre-set line pressure even when motor is not running. Allows continuous pressure adjustments and features flexible hoses with quick disconnect dry-lock couplings. Mounted in a tough protective frame, with two transport handles. Operating electricity requirement is 230V 50Hz.
- iv. Light weight aluminium reducing inserts (8 inserts per set including 6 inserts for pipes and 2 inserts for fittings) sizes 200,225,250,280,315,355,400,450mm.
- v. Upper fitting clamp 500mm for short fittings.
- vi. Stub end device with size range 200 to 500 mm.
- vii. A Generator of adequate capacity.
- viii. A 2 year warranty to cover all the equipments offered.

ANNEX A

Table 2 – Characteristics of the PE compound as granules

Characteristics	Requirements^a	Test parameters		Test method
Compound density	> 930 kg/m ^b	Test temperature Number of Samples	23 ⁰ C shall conform to ISO 1183:1987	ISO 1183:1987
Carbon black content (black compound)	(2 to 2, 5)% by mass	Shall conform to ISO 6964:1986		ISO 6964:1986
Carbon black dispersion (black compound)	< grade 3	Shall conform to ISO 18553:2002 ^c		ISO 18553:2002
Pigment dispersion (blue compound)	< grade 3	Shall conform to ISO 18553:2002 ^c		ISO 18553:2002
Water content ^b	< 300 mg/kg	Number of test pieces ^d	1	EN 12118
Volatile content	< 350 mg/kg	Number of test pieces ^d	1	EN 12099
Oxidation induction time	< 20 min	Test temperature Number of test pieces ^d	200 ⁰ C ^e 3	EN 728
Melt mass-flow rate (MFR) for PE 40	0, 2 to 1,4 g/10 min Maximum deviation of + 20% of the nominated value	Load Test temperature Time Number of test pieces ^d	2,16 kg 190 ⁰ C 10 min shall confirm to EN ISO 1133:1999	EN ISO 1133:1999, Condition D
Melt mass-flow rate (MFR) for PE 63, PE 80 and PE 100	0, 2 to 1,4 g/10 min Maximum deviation of + 20% of the nominated value	Load Test temperature Time Number of test pieces ^d	5 kg 190 ⁰ C 10 min shall confirm to EN ISO 1133:1999	EN ISO 1133:1999, Condition T
^a Conformity to these requirements shall be proved by the compound manufacture.				
^b Only applicable if the measured volatile content is not in conformity with its specified requirement. In case of dispute the requirement for water content shall apply. An alternative test method ISO 760:1978 [2] [7] may be used.				
^c In case of dispute the test pieces for carbon black dispersion and pigment dispersion shall be prepared by the compression method.				
^d The number of test pieces given indicate the quantity required to establish a value for the characteristic described in the table. The number of test pieces required for factory production control and process control should be listed in the manufacturer's quality plan (for guidance see prCEN/TS 12201-7[7]).				

Table 3 - Physical Characteristics of PE Pipes

<u>Characteristics requirements</u>	<u>Requirements</u>	<u>Test parameters</u>		<u>Test method</u>
Elongation at break for $e < 5$ mm	> 350%	Test piece shape speed of test number of test pieces ^a	Type 2 100 mm/min shall confirm to EN ISO 6259-1:2001	EN ISO 6259-1:2001 and ISO 6259-3:1997
Elongation at break for $5 \text{ mm} < e < 12$ mm	> 350%	Test piece shape speed of test number of test pieces ^a	Type 1 ^b 50 mm/min shall confirm to EN ISO 6259-1:2001	EN ISO 6259-1:2001 and ISO 6259-3:1997
Elongation at break for $e > 12$ mm	> 350%	Test piece shape speed of test number of test pieces ^a	Type 1 ^b 25 mm/min shall confirm to EN ISO 6259-1:2001	EN ISO 6259-1:2001 and ISO 6259-3:1997
		OR		
		Test piece shape Speed of test Number of test pieces ^a	Type 3 ^b 10 mm/min shall confirm to EN ISO 6259-1:2001	
Melt mass-flow rate MFR for PE 40	Change of MFR by processing + 20% ^c	Load Test temperature Time Number of test pieces ^a	2,16 kg 190 ⁰ C 10 min shall confirm to EN ISO 1133:1999	EN ISO 1133:1999, Condition D
Melt mass-flow rate MFR for PE 63, PE 80 and PE 100	Change of MFR by processing + 20% ^c	Load Test temperature Time Number of test pieces ^a	5 kg 190 ⁰ C 10 min shall confirm to EN ISO 1133:1999	EN ISO 1133:1999, Condition T
Oxidation induction time	> 20 min	Test temperature Number of test pieces ^{a, d}	200 ⁰ C ^e 3	EN 728
Effect on water quality ^f	National regulations apply			
^a The number of test pieces given indicate the quantity required to establish a value for the characteristic described in the table. The number of test pieces required for factory production control and process control should be listed in the manufacturer's quality plan (for guidance see preCEN/TS 12201-7[3]).				
^b Where practical machined type 2 test pieces may be used for pipe wall thickness < 25 mm. The test may be terminated when the requirement is met, without continuing until the rupture of the test piece.				
^c Value as measured on the pipe relative to the value measured on the compound used.				
^d Samples to be taken from the inner wall surface.				
^e Test may be carried out as an indirect test at 210 ⁰ C providing that there is clear correlation of the results to those at 200 ⁰ C : in cases of dispute the reference temperature shall be 200 ⁰ C.				

Table 4 - Mechanical Characteristics of PE Pipes

<u>Characteristics requirements</u>	<u>Requirements</u>	<u>Test parameters</u>		<u>Test method</u>
		<u>Parameters</u>	<u>Value</u>	
Hydrostatic strength at 20 ⁰ C	No failure during test period of any test pieces	End caps Conditioning period Number of test pieces ^b Type of test Test temperature Test period Circumferential (hoop) stress for : PE 40 PE 63 PE 80 PE 100	Type a) ^a Shall confirm to EN921:1994 3 Water-in-water 20 ⁰ C 100 h 7,0 MPa 8,0 MPa 10,0 MPa 12,4 MPa	EN921:1994
Hydrostatic strength at 80 ⁰ C	No failure during test period of any test pieces	End caps Conditioning period Number of test pieces ^b Type of test Test temperature Test period Circumferential (hoop) stress for : PE 40 PE 63 PE 80 PE 100	Type a) ^a Shall confirm to EN921:1994 3 Water-in-water 80 ⁰ C 165 h 2,5 MPa 3,5 MPa 4,5 MPa 5,4 MPa	EN921:1994
Hydrostatic strength at 80 ⁰ C	No failure during test period of any test pieces	End caps Conditioning period Number of test pieces ^b Type of test Test temperature Test period Circumferential (hoop) stress for : PE 40 PE 63 PE 80 PE 100	Type a) ^a Shall confirm to EN921:1994 3 Water-in-water 80 ⁰ C 1000 h 2,0 MPa 3,2 MPa 4,0 MPa 5,0 MPa	EN921:1994

^a Type b) end caps may be used for batch release tests for diameters > 500 mm.

^b The number of test pieces given indicate the quantity required to establish a value for the characteristic described in the table. The number of test pieces required for factory production control and process control should be listed in the manufacturer's quality plan (for guidance see prCEN/TS 12201-7[3]).

^c Premature ductile failures are not taken into account. For retest procedure see Clause 7.3 of BSEN 12201-2:2003

Table 5 - Physical Characteristics of PE Fittings

Characteristics requirements	Requirements	Test parameters		Test method
		Parameters	Value	
Melt mass-flow rate (MFR) for PE 40	Change of MFR by processing + 20% ^{b)}	Load Test temperature Test period Number of test pieces ^{a)}	2,16 kg 190 ⁰ C 10 min shall confirm to EN ISO 1133:1999	EN ISO 1133:1999, condition D
Melt mass-flow rate (MFR) for PE 463, PE 80 and PE 100	Change of MFR by processing + 20% ^{b)}	Load Test temperature Test period Number of test pieces ^{a)}	5 kg 190 ⁰ C 10 min shall confirm to EN ISO 1133:1999	EN ISO 1133:1999, condition T
Oxidation induction time	> 20 min	Test temperature Number of test pieces ^{a)}	200 ⁰ C ^{c)} 3	EN 728
Cohesive resistance for electro fusion socket fittings	Length of initiation rupture < L ₂ /3 in brittle failure	Test temperature Number of test pieces ^{a)}	23 ⁰ C shall confirm to ISO 13954:1997	ISO 13954:1997
		OR		
Cohesive resistance for electro fusion socket fittings	Surface rupture: > 25%, brittle failure	Test temperature Number of test pieces ^{a)}	23 ⁰ C as specified in ISO/DIS 13956:1996	ISO/DIS 13956:1996
Tensile strength for butt fusion fittings – spigoted fittings	Test to failure : Ductile :pass Brittle :fail	Test temperature Number of test pieces ^{a)}	23 ⁰ C as specified in ISO/DIS 13953:2001	ISO 13953:2001
Impact resistance of tapping tees	No failure, no leaks	Test temperature Mass of striker Height Conditioning period: in air in liquid	(0 + 2) ⁰ C (2500 + 20) g (2000 + 10) mm 4 h 2 h	EN 1716
Effect on water quality		National regulations apply		
^{a)} The number of test pieces given indicate the quantity required to establish a value for the characteristic described in the table. The number of test pieces required for factory production control and process control should be listed in the manufacturer's quality plan for guidance see prEN/TS 12201-7[7].				
^{b)} Value as measured on the fitting relative to the value measured on the compound used.				
^{c)} Test may be carried out as an indirect test at 210 ⁰ C providing that there is clear correlation of the results to those at 200 ⁰ C : in cases of dispute the reference temperature shall be 200 ⁰ C.				

Table 6 - Mechanical Characteristics of PE Fittings

<u>Characteristics requirements</u>	<u>Requirements</u>	<u>Test parameters</u>		<u>Test method</u>
		<u>Parameters</u>	<u>Value</u>	
Hydrostatic strength at 20 ⁰ C	No failure during test period of any test pieces	End caps Conditioning period Number of test pieces ^b Type of test Test temperature Test period Circumferential (hoop) stress ^c for : PE 40 PE 63 PE 80 PE 100	Type a) ^a Shall confirm to EN921:1994 3 Water-in-water 20 ⁰ C 100 h 7,0 MPa 8,0 MPa 10,0 MPa 12,4 MPa	EN921:1994
Hydrostatic strength at 80 ⁰ C	No failure during test period of any test pieces	End caps Conditioning period Number of test pieces ^b Type of test Test temperature Test period Circumferential (hoop) stress ^c for : PE 40 PE 63 PE 80 PE 100	Type a) ^a Shall confirm to EN921:1994 3 Water-in-water 80 ⁰ C 165 h ^d 2,5 MPa 3,5 MPa 4,5 MPa 5,4 MPa	EN921:1994
Hydrostatic strength at 80 ⁰ C	No failure during test period of any test pieces	End caps Conditioning period Number of test pieces ^b Type of test Test temperature Test period Circumferential (hoop) stress ^c for : for : PE 40 PE 63 PE 80 PE 100	Type a) ^a Shall confirm to EN921:1994 3 Water-in-water 80 ⁰ C 1000 h 2,0 MPa 3,2 MPa 4,0 MPa 5,0 MPa	EN921:1994
^a Type b) end caps may be used for batch release tests for diameters > 500 mm.				
^b The number of test pieces given indicate the quantity required to establish a value for the characteristic described in the table. The number of test pieces required for factory production control and process control should be listed in the manufacturer's quality plan (for guidance see prCEN/TS 12201-7[7]).				
^c The stress shall be calculated using the dimensions of the pipe used in the test assembly.				
^d Premature ductile failures are not taken into account. For retest procedure see Clause 7.4 of BSEN 12201-3:2003				

Note : Loop of sling should be adequately long and strong for lifting the coil




Fig. 1 - SLING ARRANGEMENT FOR LIFTING 63 mm ϕ COILS

